

Test Report

No. 2218443/JL

Date : Aug 05 2011

Page 1 of 3

NEW ERA RESOURCES LTD.
 RM 1701-2, SHANGHAI INDUSTRIAL INVESTMENT BUILDING,
 NO.60 HENNESSY ROAD,
 WANCHAI, HONG KONG

The following sample was submitted and identified on behalf of the client as
 MICROMATE – ALUMINIUM COOKWARE.

SGS Job No. : 3934439
 Item No. : MMP254088A
 Supplier/ Manufacturer : NEW ERA RESOURCES LTD.
 Country of Origin : CHINA
 Sample Receiving Date : JUL 26 2011
 Testing Period : JUL 26 – AUG 02 2011


Test Requested : Please refer to the result summary.

Test Method & Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
1. Council of Europe Resolution AP (2004) 1.	--
a) Organic Coating – Overall migration	PASS
2. German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 and BfR recommendation. (Selected tests as specified by client)	--
a) Non-stick coating – Specific migration of Perfluorooctanoic acid (PFOA)	PASS

Signed for and on behalf of
 SGS Hong Kong Ltd.



Choi Man Kit, Andy
 Section Manager

Test Report

No. 2218443/JL

Date : Aug 05 2011

Page 2 of 3

Test Results :

1. Council of Europe Resolution AP (2004) 1

a) Organic Coating – Overall migration

Method : With reference to EN 1186-1:2002 for selection of conditions and test methods;
EN 1186-9:2002 aqueous food simulants by article filling method;
EN 1186-14:2002 substitute test.

Simulant Used	Test Condition	Result (mg/kg)	Detection Limit (mg/kg)	Permissible Limit (mg/kg)
		1		
3% Acetic Acid (W/V) Aqueous Solution	2 hours at 100°C	ND	5.0	60
50% Ethanol (V/V) Aqueous Solution	2 hours at 100°C	ND	5.0	60
Fatty food substitute				
95% Ethanol	6 hours at 60°C	ND	5.0	60
Isooctane	4 hours at 60°C	ND	5.0	60
Comment	--	PASS	--	--

Sample Description :

1. Black Coated Metal

Note : 1. mg/kg = milligram per kilogram of foodstuff in contact with
2. °C = degree Celsius
3. ND = Not Detected

2. German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 and BfR recommendation.

a) Non-stick coating – Specific migration of Perfluorooctanoic acid (PFOA)

Method : Sample Preparation with reference to EN13130-1:2002, followed by analysis using Liquid Chromatography Mass Spectrometry (ICP).

Simulant Used	Test Condition	Result (mg/dm ²)	Detection Limit (mg/dm ²)	Permissible Limit (mg/dm ²)
		1		
3% Acetic Acid (W/V) Aqueous Solution	60 minutes at 95°C	ND	0.002	0.005
Comment	--	PASS	--	--

Sample Description :

1. Black Coated Metal

Note : 1. mg/dm² = milligram per square decimeter
2. °C = degree Celsius
3. ND = Not Detected

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested *and such sample(s) are retained for 30 days only.*